

SABIC[®] LDPE 1965N0

LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC[®] LDPE 1965N0 is an additive free standard CTR[®] tubular grade with a high flow rate for masterbatch. This grade has a high filler acceptance.

Application

SABIC[®] LDPE 1965N0 is a masterbatch grade typically used for injection moulding applications, where high filler acceptance and good flow properties are required.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

Revision 20190507

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190 °C and 5 kg	205	dg/min	ISO 1133
at 190 °C and 2.16 kg	65	dg/min	ISO 1133
Melt volume rate (MVR)			
at 190 °C and 5 kg	270	ml/10 min	ISO 1133
at 190 °C and 2.16 kg	85	ml/10 min	ISO 1133
Density	919	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile test ^{(1) (2)}			
stress at break	7	MPa	ISO 527-2
tensile modulus	165	MPa	ISO 527-2
strain at break	150	%	ISO 527-2
stress at yield	8	MPa	ISO 527-2
Creep modulus ^{(3) (4)}			
after 1000 hours	35	MPa	ISO 899
after 1 hour	70	MPa	ISO 899
Izod impact notched			
at 23 °C	40	kJ/m ²	ISO 180/A
at -30 °C	5.0	kJ/m ²	ISO 180/A
Hardness Shore D	40	-	ISO 868
THERMAL PROPERTIES			
Heat deflection temperature ⁽⁵⁾			
at 1.80 MPa (HDT/A)	40	°C	ISO 75-2
Vicat Softening Temperature			
at 10 N (VST/A)	75	°C	ISO 306
DSC test			
melting point	104	°C	DIN 53765
enthalpy change	100	J/g	DIN 53765

- (1) Test specimen according to ISO 527-2 type 1BA, thickness 2 mm
- (2) Speed of testing: 50 mm/min
- (3) Test specimen according to ISO 3167, thickness 4 mm
- (4) Determined at 23 °C, 3 MPa
- (5) Conditioning of test specimen: temp. 23 °C, relative humidity 50 %, 24 hours

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO 9001.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet (www.SABIC.com). Additional specific information can be requested via your local Sales Office.

ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.